

# PLANOCOLOR ANTICO



## Micro cement coating for walls & ceilings

- **▷** Excellent workability
- Resistant to weather conditions
- High aesthetics
- Suitable for applications in wet areas
- Ideal for renovations

| _          |     |     |      |
|------------|-----|-----|------|
| Des        | cri | ntı | n    |
| <b>DC3</b> |     | vu  | ,,,, |

PLANOCOLOR ANTICO is a fine-grained cement mortar with excellent workability for applications in both internal and external areas in walls and ceilings. Due to the composition of the material, it is possible to add the special sand PLANOCOLOR KURASANI ADDITIVE to create coatings with rich texture and high aesthetics.

### **Certifications**

CE Marking with Declaration of Performance (DoP) C08062-CPR-2370022 as a general-purpose rendering mortar for applications in internal and external walls, columns and partitions according EN 998-1, CSIV.

### **Typical Applications**

### PLANOCOLOR ANTICO is suitable for:

- Creating decorative coatings of high aesthetics in texture and appearance creating decorative micro-cement coatings with very smooth finish
- With a showcase of PLANOCOLOR KURASANI ADDITIV for creating traditional texture and appearance

### Advantages

- Easy to apply
- It gives different aesthetic results
- Breathing
- Suitable for wet rooms, bathrooms, etc.

For applications in various substrates such as:

- Concrete, cement screed mortars
- Renders and masonry mortars
- Cement and gypsum boards (with appropriate primer)

www.novamix.gr 1 / 4



### **Technical Data**

### **Product Identification**

| Consistency - Color | Powder - white                                 |
|---------------------|--|
| Chemical base       | Portland cement, aggregates, special additives |
| Granulometry        | D <sub>max</sub> : 0,2 mm                      |
| Apparent weight     | 1,3 ± 0,1 kg/L                                 |

### **Application Data (+23°C % & 50% R.H.)**

| Mixing ratio                | 6 – 6,5 L water per 20 kg |
|-----------------------------|---------------------------|
| Specific gravity of the mix | 1,50 ± 0,05 kg/L          |
| Dry mortar density          | 1,45 ± 0,05 kg/L          |
| Temperature application     | from +5°C up to +35°C     |
| Pot life                    | 3 – 4 hours               |

### Final Performances according to EN 998-1:2016

|  | Performance                     |
|--|---------------------------------|
| Compressive strength                               | ≥ 10 N/mm <sup>2</sup>          |
| Adhesion   | ≥ 1,0 N/mm <sup>2</sup>         |
| Capillary water absorption                         | ≤ 0,40 kg/m²·min <sup>0,5</sup> |
| Water vapour permeability coefficient (µ)          | µ ≤ 20                          |
| Thermal conductivity mean $(\lambda_{10,dry,mat})$ | 0,45 W/mk                       |

### **Application Procedure**

### **Substrate preparation**

Cement based substrates must be compact, without cracks, free of dust, salts, grease and any other materials that could reduce adhesion of PLANOCOLOR ANTICO to them. Concrete substrates should be mechanically prepared, for example by grinding, to achieve a uniform surface of open porosity without protruding edges. For gypsum-based substrates, it is necessary to prime the substrate with NOVAPRIMER. Non-absorbent substrates are recommended to be primed with PLANO CONTACT FAST or SC ELASTIC. For more information, please refer to the relative Technical Data Sheets of the products.

www.novamix.gr 2 / 4



| Preparation of the |  |
|--------------------|--|
|                    |  |
|                    |  |

Mix the PLANOCOLOR ANTICO bag (20 kg) with 6.0-6.5 liters of clean water with a low-speed electric mixer for at least 3-5 minutes. Mixing should take place until the mixture is completely uniform and free of lumps. It is recommended to mix the pigment first with water. To achieve the shade of the PLANOCOLOR color chart, a PLANOCOLOR DESIGN A/V pigment is mixed with every 10 kg PLANOCOLOR ANTICO. The product is ready for use. The mixture has approximately 3-4 hours of pot life.

The 25 kg case of PLANOCOLOR KURASANI ADDITIVE are recommended to be added after the addition of PLANOCOLOR ANTICO to water, where the quantity is increased to 6 - 7 liters.

### **Application**


The mix is applied with a trowel in one or more layers at a total thickness not exceeding 5 mm, with a maximum per coat thickness of 2 mm. The waiting time between layers must be 2 - 3 hours depending on the temperature and the humidity of the environment.

### Recommendations

- Do not apply when substrate and ambient temperatures are below +5°C and higher than +35°C
- Do not apply upon metal or wood or surfaces such as polyurethane, acrylic, paints and substrates subjected to big movements
- Do not apply upon PVC membranes, bituminous membranes and other materials that polymerize in the long ran
- Do not apply upon loose substrates or substrates with insufficient cure
- Do not apply upon non-absorbent substrates without proper preparation
- Do not cover existing expansion joints of the substrate
- Do not apply during direct sunlight and/or strong wind presence
- Do not exceed the recommended quantity of the mixing water and of 25 kg of PLANOCOLOR KURASANI ADDITIV per 20 kg of PLANOCOLOR ANTICO
- Protect from rain or frost the first 24 hours
- Do not add cement, gypsum, lime or other additives that might affect the properties of the mortar
- Application to be performed by professional users

# Cleaning Buckets, tools, coatings etc. can be cleaned with water as long as the mix is still fresh. Once dried cleaning can be done only by mechanical means PLANOCOLOR ANTICO remains stable for at least 12 months in the original sealed packaging stored in a dry place and temperature between +5°C and +35°C. Packaging Paper bags of 20 kg

www.novamix.gr 3 / 4





### **Safety Instructions**

For information and instructions regarding disposal and safe handling, users should refer to the latest Safety Data Sheet of the product containing ecological, toxicological and other safety-related data.

### Legal notes

The technical data and recommendations contained or listed in this leaflet are the result of laboratory measurements, of our current knowledge and experience. All the above-mentioned information and specifications should in any case be considered as indicative, as they may differ from each other. The Company makes every effort to ensure the accuracy of the information provided herein. Product specifications, prices and availability are subject to change without notice and may differ from those shown.

In practice, variations in materials, substrates and on-site implementation conditions are such that no warranty can be given or implied, as to the merchantability or suitability of the materials for a particular purpose and for the exact conditions of each project. Anyone interested of using the product must be sure beforehand that the product is suitable for the intended use and in any case, the user is solely responsible for any consequences due to the use of the product. Among other things, the Company is not responsible for any normal wear or tear from environmental or other inappropriate conditions. We reserve the right to revise or change the data herein without prior notice.

Restrictions and disclaimers apply to the extent permitted by applicable law. The Company has a Technical Support Department, which is the only one responsible for providing technical advice and solutions to deal with problems. Requests to the Technical Support Department are addressed and answered, only in writing.

For the latest and a valid version of the Technical Data Sheet, the user of the material must refer to our website www.novamix.gr or directly to the QR Code of the product.













DOMOCHEMICAL S.A. 40 Papanikoli str. Chalandri, 15232, Athens T +30 210 68 93 953 F +30 210 68 94 571 novamix@novamix.gr

4/4 www.novamix.gr